

Sicostirolo[®] 684

High Impact Polystyrene
Prime Compound

Description:

HIPS V0 flame retardant grade PBDE free

General

MFI (200°C/5kg)	ISO 1133	6	g/10min
Density	ISO 1183	1.16	g/cm ³
Linear mould shrinkage	ISO 2577	0.4-0.6	%

Thermal

HDT/A (1,82MPa)	ISO 75A	81	°C
Vicat softening point (B50 (50°C/h, 50N))	ISO 306	90	°C
Vicat softening point (A50(50°C/h, 10N))	ISO 306	98	°C

Mechanical

Tensile stress at yield	ISO 527	25	MPa
Tensile stress at break	ISO 527	22	MPa
Elongation at break	ISO 527	30	%
Flex modulus	ISO 178	2200	MPa
Izod impact (+23°C (notched))	ISO 180/1A	8	kJ/m ²

Flammability

Flammability (3,2mm)	UL94	V0	
Flammability (1,6mm)	UL94	V0	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	960	°C

Various

Surface resistivity	IEC 60093	1.00E+15	Ohm
Volume resistivity	IEC 60093	1.00E+15	Ohm.cm
Dielectric rigidity (Oil 1mm)	IEC 60243-1	50	kV/mm
CTI	IEC 60112	400	V

Remark:

UL94 officially approval file number: E103497

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. It is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

Ravago Group Headquarters